

Table 1 Mean projected areas of 3T3 cell populations on glass and silane

Surface treatment and incubation time	Area (μm^2)	Percentage of cells with areas $< 500 \mu\text{m}^2$
Glass, 0.5 h	526 \pm 274	57 (N = 3; n = 344)
Glass, 2 h	746 \pm 753	44 (N = 10; n = 1419)
Glass Fn, 0.5 h	902 \pm 274	31 (N = 5; n = 827)
Glass Fn, 1 h	997 \pm 888	34 (N = 10; n = 1518)
Glass Fn, 2 h	2190 \pm 2150	14 (N = 10; n = 1437)
Silane, 0.5 h	818 \pm 587	35 (N = 3; n = 318)
Silane, 2 h	1150 \pm 1190	33 (N = 8; n = 956)
Silane Fn, 2 h	3357 \pm 2675	1 (N = 1; n = 106)

Values are mean \pm standard deviation.

N, number of experiments; n, number of cells examined.